



(19)

(11) Publication number: **07029823 A**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**(21) Application number: **05154049**(51) Intl. Cl.: **H01L 21/203 H01L 21/331 H01L 29/73**(22) Application date: **25.06.93**

<p>(30) Priority:</p> <p>(43) Date of application publication: <b>31.01.95</b></p> <p>(84) Designated contracting states:</p>	<p>(71) Applicant: <b>NEC CORP</b></p> <p>(72) Inventor: <b>TAKANO HIROSHI</b></p> <p>(74) Representative:</p>
---	--

**(54) FABRICATION OF SEMICONDUCTOR DEVICE**

(57) Abstract:

**PURPOSE:** To shorten the fabrication process of semiconductor device, when epitaxial growth of silicon is conducted selectively by irradiating a silicon substrate with a molecular beam of silicon using a solid source, by simultaneously irradiating the silicon substrate with a molecular beam of solid halide compound.

**CONSTITUTION:** Silicon oxide 12 is deposited on an n+ type silicon substrate 11 and then an opening 13 is made therein. The silicon substrate 11 is then set on a rotary substrate heating table 2 in a growth chamber 1. Subsequently, the silicon substrate 11 is irradiated simultaneously with molecular beams of silicon, P type impurities and a solid halide compound, i.e., XeF<sub>2</sub> (or XeF<sub>4</sub>) by means of an E gun 3 for Si, a K cell 4 and a K cell 5 for solid halide compound. Consequently, silicon is grown selectively and an epitaxial film 14 is formed at the opening 13.

COPYRIGHT: (C)1995,JPO

